

TEST REPORT

Report No. : MAN:HL:1048006161

DATE : 09th August, 2019



DAMATI PLASTICS

FLAT NO-05, 2ND FLOOR, PUSHPA KUNJ BUILDING, OPPOSITE-THADOMAL SAHANI
ENGINEERING COLLEGE WEST(TSEC), 37th ROAD, BANDRA WEST,
MUMBAI-400050
INDIA

CONTACT PERSON : MR. SANAD UPADHYAY

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION	PLASTICS RECTANGULAR & ROUND CONTAINER WITH LID.
COLOUR	BLACK, WHITE & TRANSPARENT
STYLE NO.	DP-750ML-MANGO, DP-1000ML-MANGO, DP-1250ML-MANGO, RE-342 & RE-232
SAMPLE RECD ON	02/08/2019
TEST PERFORMING DATE	02/08/2019 TO 08/08/2019

SUMMARY OF TEST RESULTS:

TEST REQUESTED	CONCLUSION
Testing as per Commission Regulation (EU) No. 10/2011 of 14 January 2011.	--
Overall Migration	Pass

TEST(S) RESULT & METHOD: PLEASE REFER TO NEXT PAGE(S)

Per Pro SGS India Pvt. Ltd.



Sandip Bhushan (Asst. Manager)

Authorized Signatory

Email your Test Report Related Enquiries at Feedback.HLT@sgs.com

TEST REPORT

Report No. : MAN:HL:1048006161

DATE : 09th August, 2019



TEST RESULTS :-

Testing as per Commission Regulation (EU) No 10/2011:

Overall migration:

Method: With reference to Commission Regulation (EU) No 10/2011 of 14 January 2011 Annex III and Annex V for selection of condition and EN 1186-1:2002 for selection of test methods (1st Migration);
EN 1186-9:2002 aqueous food simulants by article filling method;

Simulant Used	Test Condition	Result (mg/dm ²)	Reporting Limit (mg/dm ²)	Permissible Limit (mg/dm ²)
3% Acetic Acid	40°C for 2 hours	ND	2.0	10
10% Ethanol	40°C for 2 hours	ND	2.0	10
Conclusion	--	Pass	--	--

Sample Description: Plastics Rectangular & Round Container


Note :-

1. mg/dm² = milligram per square decimeter
2. °C = degree Celsius
3. ND = Not Detected
4. Permissible Limit is according to Commission Regulation (EU) No 10/2011 of 14 January 2011 with amendments.
5. Testing has been subcontracted to SGS approved Lab.
6. Testing has been performed as per client's request.

Remark :-

1. Analytical tolerance of aqueous simulants is 2mg/dm² or 12mg/kg
2. Test condition & simulant were specified by client.

Samples as Received (Tested Item)



TEST REPORT

Report No. : MAN:HL:1048006161

DATE : 09th August, 2019



Samples as Received (Grouped Item)



***** End of Report*****